

# **2023 Pavement Condition Report** For Van Buren County, Michigan



Prepared by the Southwest Michigan Planning Commission 376 W Main St Benton Harbor, MI 49022 (269) 925-1137

Overview of The PASER Rating System	.3
Summary of Cass County 2021 Ratings	. 5
Countywide Trends in Pavement Conditions	. (
Road Miles Within Berrien County	. 7
Summary Ratings by Jurisdiction	.8
PASER Rating Charts	11


For more information visit: <a href="www.michigan.gov/tamc">www.michigan.gov/tamc</a>
Questions about this report can be sent to:
Brandon Kovnat, SWMPC Associate Planner
<a href="www.michigan.gov/tamc">kovnath@swmpc.org</a>
(269) 925-1137 x 1524

## Overview of the PASER Rating Process and System

Each year, the Southwest Michigan Planning Commission collaborates with the Van Buren County Road Commission to assess the pavement condition of federal aid eligible roads in Van Buren County. This evaluation process follows the guidelines established by the Michigan Transportation Asset Management Council (TAMC).

The assessment utilizes the Pavement Surface Evaluation and Rating system (PASER), with TAMC mandating that pavement data be evaluated by teams comprised of a minimum of two certified members. Since 2008, TAMC has required that half of the federal aid eligible roads in each county be rated biennially, with two years of ratings covering 100% of a county's federal aid eligible roads. In response to COVID-19, rating requirements were waived for 2020, with a full assessment conducted in 2021. Half-county ratings resumed in 2022.

In 2023, assessment of the Federal-Aid eligible roads in the southern portion of Van Buren County took place, while the northern portion was last evaluated in 2022.




## Pavement Surface Evaluation and Rating System

The <u>Pavement Surface Evaluation and Rating</u> (PASER) system is a visual survey method for evaluating the condition of roads on a scale of 1 to 10, with 1 being a pavement in a failed condition and 10 being a pavement in excellent condition. Guidelines for rating the pavement surface using the PASER system in Michigan have been developed by the <u>Michigan Transportation Asset Management Council</u> (TAMC). The TAMC groups the 1-to-10 rating scale into three categories (Good 8-10, Fair 5-7, Poor 1-4) based on the type of work that is typically required for each rating grouping (routine maintenance, preventive maintenance, or reconstruction).



PASER Rating 8-10
Requires Routine Maintenance




PASER Rating 5-7 Requires Capital Preventative Maintenance



PASER Rating 1-4
Requires Structural Improvements
or Reconstruction


The costs of rehabilitation are exponentially higher than the costs of preventative maintenance, a full reconstruction being the most expensive treatment option. Asset management best practices encourage preventative maintenance to slow decay and reduce costs.



It Is necessary to know the pavement condition of roads when planning for future maintenance; this allows for more accurate estimates of the treatment costs and ensures fewer roads reach the critical distress point (CDP) – the point at which maintenance is no longer effective.


# Summary of Van Buren County 2022/2023 Ratings

2022/2023 All Federal Aid Miles by PASER Rating



The most common PASER was eight, which accounts for approximately 27% of all roads.


## 2022/2023 Local and MDOT Maintained Federal Aid Miles by PASER




Locally maintained roads are, in general, in worse condition than MDOT maintained roads. This is largely due to federal and state funding being prioritized first for interstate maintenance and then for the other highways and major arterials. These higher traffic roads are primarily maintained by MDOT, compared to the roads classified as minor arterials and collects which are maintained primarily by local road agencies.

## Countywide Trends in Pavement Conditions

Ten-Year Trend in Countywide PASER Ratings 2014-2023 Includes City, Village, Road Department, and MDOT Maintained Roads



Changes in Good, Fair, and Poor Ratings Over the Last Ten Years Includes City, Village, Road Department, and MDOT Maintained Roads



## Road Miles within Van Buren County


	T . 1	Non		Federal Aid	
Jurisdiction	Total Miles	Federal Aid	Total	Locally Owned	MDOT Owned
City of Bangor	17.3	13.6	3.7	2.4	1.3
City of Hartford	15.1	11.3	3.7	3.1	0.7
City of South Haven	5.1	2.8	2.3	2.3	-
Village of Bloomingdale	4.0	2.8	1.3	1.3	-
Village of Breedsville	17.0	13.7	3.3	2.1	1.3
Village of Decatur	5.9	3.7	2.2	1.3	0.9
Village of Gobles	7.8	5.1	2.7	2.7	-
Village of Lawrence	17.9	13.2	4.7	3.1	1.6
Village of Lawton	25.6	13.9	11.7	7.0	4.7
Village of Mattawan	27.1	17.6	9.5	3.4	6.1
Village of Paw Paw	43.2	23.8	19.4	13.8	5.6
Almena Twp	85.7	66.7	19.0	13.2	5.9
Antwerp Twp	100.4	67.6	32.8	22.6	10.2
Arlington Twp	75.9	59.1	16.7	11.0	5.7
Bangor Twp	81.9	70.0	12.0	9.9	2.1
Bloomingdale Twp	81.5	67.1	14.3	11.9	2.4
Columbia Twp	89.7	70.5	19.2	19.2	-
Covert Twp	91.6	54.5	37.1	15.1	22.0
Decatur Twp	67.0	56.4	10.6	7.1	3.4
Geneva Twp	83.0	64.1	18.9	14.8	4.1
Hamilton Twp	69.1	45.2	23.9	17.4	6.4
Hartford Twp	76.5	51.6	24.9	12.6	12.3
Keeler Twp	75.6	57.0	18.5	14.6	3.9
Lawrence Twp	89.4	54.8	34.7	21.6	13.1
Paw Paw Twp	99.9	70.9	29.0	14.4	14.6
Pine Grove Twp	75.0	59.0	16.1	12.9	3.1
Porter Twp	77.4	58.6	18.8	12.3	6.5
South Haven Twp	73.0	36.0	37.0	16.4	20.6
Waverly Twp	72.4	51.9	20.5	8.5	12.0
Total	1,651.2	1,182.7	468.5	298.0	170.4

Roads within city and village limits are maintained by the city or village in which they lie, excluding MDOT owned roads. Roads within townships are maintained by the Van Buren County Road Commission, excluding the MDOT maintained roads. MDOT maintains all Interstates (e.g. I-94), US routes (e.g. US 12), and M-routes (e.g. M-60). Federal Aid roads are classified by the Federal Highway Administration (FHWA) as roads that serve through traffic as opposed to roads that only access properties (similar to, and in many cases the same as, the state designated primary roads). All MDOT maintained roads are classified as federal aid roads.

# Summary of Ratings by Jurisdiction

2022/2023 All Federal Aid Road Ratings

Includes City, Village, Van Buren County Road Commission, and MDOT Maintained Roads




## Federal Aid Eligible Roads Miles Rated

<sup>1</sup> Rated in 2022	239.6 miles
<sup>2</sup> Rated in 2021	228.6 miles
Total rated in 2021 & 2022	468.2 miles

#### 2022/2023 Locally Maintained Federal Aid Road Ratings


Includes City, Village, and Van Buren County Road Commission Maintained Roads



#### Locally Maintained Federal Aid Eligible Roads Miles Rated

<sup>1</sup> Rated in 2022	155.1 miles
<sup>2</sup> Rated in 2023	144.1 miles
Total rated in 2022 & 2023	299.2 miles

2022/2023 MDOT Maintained Federal Aid Road Ratings



Note: The villages of Bloomingdale Breedsville, Hartford, Lawrence, and Columbia Township do not contain any roads maintained by MDOT.

#### MDOT Maintained Federal Aid Eligible Roads Miles Rated

<sup>1</sup> Rated in 2022	84.5 miles
<sup>2</sup> Rated in 2023	84.5 miles
Total rated in 2022 & 2023	169 miles

# PASER Asphalt Rating Chart

Surface Rating	Visible Distress *	General Condition/ Treatment Measures
10	None	New construction.
9	None	Recent overlay; like new.
8	<ul> <li>No longitudinal cracks except reflection of paving joints.</li> <li>Occasional transverse cracks, widely spaced (40' or greater).</li> </ul>	Recent sealcoat or new road mix. Little or no maintenance required.
7	<ul> <li>Very slight or no raveling, surface shows some traffic wear.</li> <li>Longitudinal cracks (open 1/4") due to reflection or paving joints.</li> <li>Transverse cracks (open 1/4") spaced 10 feet or more apart, little or slight crack raveling.</li> <li>No patching or very few patches in excellent condition.</li> </ul>	First signs of aging.  Maintain with routine crack filling.
6	<ul> <li>Slight raveling (loss of lines) and traffic wear.</li> <li>Longitudinal cracks (open ½" – ½") due to reflection and paving joints.</li> <li>Transverse cracking (open ½" to ½") some spaced less than 10 ft.</li> <li>First sign of block cracking Slight to moderate flushing or polishing.</li> </ul>	Shows signs of aging, sound structural condition. Could extend life with sealcoat.
5	<ul> <li>Moderate to severe raveling (loss of fine and coarse aggregate).</li> <li>Longitudinal and transverse cracks (open ½") show first signs of slight raveling and secondary cracks.</li> <li>Block cracking up to 50% of surface.</li> <li>Extensive to severe flushing or polishing.</li> <li>Some patching or edge wedging in good condition.</li> </ul>	Surface aging, sound structural condition. Needs sealcoat or nonstructural overlay.
4	<ul> <li>Severe surface raveling.</li> <li>Multiple longitudinal and transverse cracking with slight ravelling.</li> <li>Longitudinal cracking in wheel path.</li> <li>Block cracking (over 50% of surface).</li> <li>Patching in fair condition.</li> <li>Slight rutting or distortions (½" deep or less).</li> </ul>	Significant aging and first signs of need for strengthening. Would benefit from recycling or overlay.
3	<ul> <li>Closely spaced longitudinal and transverse cracks often showing raveling and crack erosion.</li> <li>Severe block cracking.</li> <li>Some alligator cracking (less than 25 % of surface).</li> <li>Patches in fair to poor condition.</li> <li>Moderate rutting or distortion (1" or 2" deep).</li> <li>Occasional potholes.</li> <li>Alligator cracking (over 25 % of surface).</li> </ul>	Needs patching and major overlay or complete recycling.
2	<ul> <li>Severe distortions (over 2" deep).</li> <li>Extensive patching in poor condition.</li> <li>Potholes.</li> </ul>	Severe deterioration. Needs reconstruction with extensive base repair.
1	Severe distress with extensive loss of surface integrity.	Failed. Needs total reconstruction.

<sup>\*</sup> Note: Individual pavements will not have all of the types of distress listed for any particular rating. They may have only one or two types.

## PASER Concrete Rating Chart

10 None  10 None  11 Traffic wear in wheel path. 12 Slight map cracking or pop-outs.  13 Pop-outs, map cracking, or minor surface defects. 14 Slight surface scaling, or minor surface defects. 15 Slight surface scaling, or minor surface defects. 16 Slight surface scaling, or minor surface defects. 16 Nore extensive surface scaling. 17 Some open joints. 18 Isolated meander cracks and cracks at manholes, well-sealed. 19 Nore extensive surface scaling. 20 Some open joints. 21 Isolated transverse or longitudinal cracks, tight or well-sealed. 22 Some manhole displacement and cracking. 23 Some manhole displacement and cracking. 24 First utility patch, in good condition. 25 First noticeable settlement or heave area. 26 Moderate scaling in several locations. 26 A few isolated surface spalls. 27 Shallow reinforcement causing cracks. 28 Several corner cracks, tight or well-sealed. 29 Open (¼²² wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼²²). 30 Moderate to severe polishing or scaling over 25% of the surface. 31 High reinforcing steel causing surface spalling. 32 Some joints and cracks have begun spalling. 33 Some joints and cracks have begun spalling. 45 First signs of joint or spalling or faulting. 46 Some joints and cracks have begun spalling. 47 Some joints and cracks have begun spalling. 48 Joints and cracks have begun spalling. 49 Some joints and cracks have begun spalling. 40 First signs of joint or spalling or faulting. 51 Crepair surface defects partial depth joint reneeded. 52 Severe polishing, scaling, map cracking or spalling, > 50% of area 53 Severe polishing, scaling, map cracking or spalling. 54 Needs some full depth joints and cracks show moderate to severe spalling. 55 Severe polishing, scaling, map cracking or spalling. 56 Severe polishing, scaling, map cracking or spalling. 57 Severe polishing, scaling, map cracking or spalling. 58 Severe polishing, scaling, map cracking or spalling. 59 Severe polishing, scaling, map cracking or spalling. 50 Severe polishing. 5	ke new r slight alt d. se cracks	
Slight map cracking or pop-outs.  Pop-outs, map cracking, or minor surface defects. Slight surface scaling. Partial loss of joint sealant. Isolated meander cracks and cracks at manholes, well-sealed.  More extensive surface scaling. Some open joints. Isolated transverse or longitudinal cracks, tight or well-sealed. Some manhole displacement and cracking. First utility patch, in good condition. First noticeable settlement or heave area.  Moderate scaling in several locations. A few isolated surface spalls. Several corner cracks, tight or well-sealed. Several corner cracks, tight or well-sealed. Several corner cracks, tight or well-sealed. Open (¼² wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼²).  Moderate to severe polishing or scaling over 25% of the surface. High reinforcing steel causing surface spalling. Some joints and cracks have begun spalling. First signs of joint or spalling or faulting. Grepair surface defects partial depth joint reneeded.  Slight surface scaling. More surface wear of defects. More surface wear of defects. Recent asph overlay. Little or no maintenance requires.  First sign of transver (all tight) or utility particle scaling. Seal open join other routine mainte scaling. Seal open join other scaling. Seal open join other routine mainte sca	ke new r slight alt d. se cracks	
<ul> <li>Slight map cracking or pop-outs.</li> <li>Pop-outs, map cracking, or minor surface defects.</li> <li>Slight surface scaling.</li> <li>Partial loss of joint sealant.</li> <li>Isolated meander cracks and cracks at manholes, well-sealed.</li> <li>More extensive surface scaling.</li> <li>Some open joints.</li> <li>Isolated transverse or longitudinal cracks, tight or well-sealed.</li> <li>Some manhole displacement and cracking.</li> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (¼² wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼²).</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting.</li> <li>First signs of joint or spalling or faulting.</li> <li>First signs of joint or crack faulting (1/4²).</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>	r slight alt d. se cracks	
<ul> <li>Slight surface scaling.</li> <li>Partial loss of joint sealant.</li> <li>Isolated meander cracks and cracks at manholes, well-sealed.</li> <li>More extensive surface scaling.</li> <li>Some open joints.</li> <li>Isolated transverse or longitudinal cracks, tight or well-sealed.</li> <li>Some manhole displacement and cracking.</li> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (¼" wide) longitudinal or transverse joints and more frequent transverse cracks (some open ½").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting.</li> <li>First signs of joint or spalling.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>	alt d. se cracks	
<ul> <li>Slight surface scaling.</li> <li>Partial loss of joint sealant.</li> <li>Isolated meander cracks and cracks at manholes, well-sealed.</li> <li>More extensive surface scaling.</li> <li>Some open joints.</li> <li>Isolated transverse or longitudinal cracks, tight or well-sealed.</li> <li>Some manhole displacement and cracking.</li> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open ('\'a'' wide) longitudinal or transverse joints and more frequent transverse cracks (some open \(^{1}\'a''\).</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting.</li> <li>First signs of joint or partial depth joint repair surface defects partial depth joint reneeded.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>	alt d. se cracks	
<ul> <li>Partial loss of joint sealant.</li> <li>Isolated meander cracks and cracks at manholes, well-sealed.</li> <li>More extensive surface scaling.</li> <li>Some open joints.</li> <li>Isolated transverse or longitudinal cracks, tight or well-sealed.</li> <li>Some manhole displacement and cracking.</li> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (¼" wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>	se cracks	
More extensive surface scaling.  Some open joints.  Isolated transverse or longitudinal cracks, tight or well-sealed. Some manhole displacement and cracking. First utility patch, in good condition. First noticeable settlement or heave area.  Moderate scaling in several locations. A few isolated surface spalls. Several corner cracks, tight or well-sealed. Open (¼" wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼").  Moderate to severe polishing or scaling over 25% of the surface. High reinforcing steel causing surface spalling. Some joints and cracks have begun spalling. First signs of joint or spalling or faulting (1/4"). Multiple corner cracks with broken pieces. Moderate settlement or frost heave areas.  First sign of transver (all tight) or utility particular distribution willight or utility particular distribution or there well-sealed. First sign of transver (all tight) or utility particular distribution or the transver scaling. Sealing sealing. First sign of transvers (all tight) or utility particular distribution or the transver scaling. Sealing sealing. First sign of shallow reinforcement or core cracking. Needs generated and crack sealing. Sealing. Sealing sealing sealing sealing sealing. First signs of joint or spalling. First signs of joint or spalling or faulting. Or repair surface defects partial depth joint reneeded.	se cracks	
<ul> <li>Some open joints.</li> <li>Isolated transverse or longitudinal cracks, tight or well-sealed.</li> <li>Some manhole displacement and cracking.</li> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (¼" wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
Isolated transverse or longitudinal cracks, tight or well-sealed.  Some manhole displacement and cracking. First utility patch, in good condition. First noticeable settlement or heave area.  Moderate scaling in several locations. A few isolated surface spalls. Shallow reinforcement causing cracks. Several corner cracks, tight or well-sealed. Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").  Moderate to severe polishing or scaling over 25% of the surface. High reinforcing steel causing surface spalling. Some joints and cracks have begun spalling. First signs of joint or spalling or faulting. Grepair surface defects partial depth joint reinforced. Moderate settlement or frost heave areas.  Severe polishing, scaling, map cracking or spalling, > 50% of area		
Some manhole displacement and cracking.  First utility patch, in good condition.  First noticeable settlement or heave area.  Moderate scaling in several locations.  A few isolated surface spalls.  Shallow reinforcement causing cracks.  Several corner cracks, tight or well-sealed.  Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").  Moderate to severe polishing or scaling over 25% of the surface.  High reinforcing steel causing surface spalling.  Some joints and cracks have begun spalling.  First signs of joint or spalling or faulting (1/4").  Multiple corner cracks with broken pieces.  Moderate settlement or frost heave areas.  Severe polishing, scaling, map cracking or spalling, > 50% of area	ucn.	
<ul> <li>Some manhole displacement and cracking.</li> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting. Grepair surface defects partial depth joint remeded.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>	ce	
<ul> <li>First utility patch, in good condition.</li> <li>First noticeable settlement or heave area.</li> <li>Moderate scaling in several locations.</li> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (¼" wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¼").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting.</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Moderate scaling in several locations.         <ul> <li>A few isolated surface spalls.</li> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (¹/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open ¹/4").</li> </ul> </li> <li>Moderate to severe polishing or scaling over 25% of the surface.         <ul> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling or faulting.</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> </ul> </li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
A few isolated surface spalls.  Shallow reinforcement causing cracks. Several corner cracks, tight or well-sealed. Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").  Moderate to severe polishing or scaling over 25% of the surface. High reinforcing steel causing surface spalling. Some joints and cracks have begun spalling. First signs of joint or spalling or faulting. First signs of joint or spalling or faulting. Moderate settlement or frost heave areas.  Severe polishing, scaling, map cracking or spalling, > 50% of area		
Shallow reinforcement causing cracks.  Several corner cracks, tight or well-sealed. Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").  Moderate to severe polishing or scaling over 25% of the surface. High reinforcing steel causing surface spalling. Some joints and cracks have begun spalling. First signs of joint or crack faulting (1/4"). Multiple corner cracks with broken pieces. Moderate settlement or frost heave areas.  Severe polishing, scaling, map cracking or spalling, > 50% of area	-	
<ul> <li>Shallow reinforcement causing cracks.</li> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Several corner cracks, tight or well-sealed.</li> <li>Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Open (1/4" wide) longitudinal or transverse joints and more frequent transverse cracks (some open 1/4").</li> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or spalling.</li> <li>First signs of joint or erack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Moderate to severe polishing or scaling over 25% of the surface.</li> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>High reinforcing steel causing surface spalling.</li> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Some joints and cracks have begun spalling.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>	· crack	
<ul> <li>Some joints and cracks have begun spaning.</li> <li>First signs of joint or crack faulting (1/4").</li> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Multiple corner cracks with broken pieces.</li> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
<ul> <li>Moderate settlement or frost heave areas.</li> <li>Severe polishing, scaling, map cracking or spalling, &gt; 50% of area</li> </ul>		
Severe polishing, scaling, map cracking or spalling, > 50% of area		
• Joints and cracks show moderate to severe spalling. I Needs some full den	,	
<ul> <li>Pumping and faulting of joints (1/2") with fair ride.</li> <li>Several slabs have multiple transverse or meander cracks with moderate overlay to correct su</li> </ul>		
<ul> <li>Several slabs have multiple transverse or meander cracks with moderate spalling. Spalled area broken into several pieces.</li> <li>overlay to correct su defects.</li> </ul>	.1acc	
Corner cracks with missing pieces or patches		
Most joints and cracks are open, with multiple parallel cracks, severe		
spalling or faulting.		
D-cracking is evident  Needs extensive full		
Severe faulting (12) giving poor ride	patching plus some full slab	
Extensive patching in fair to poor condition.  replacement.		
Many transverse and meander cracks, open and severely spalled.		
Extensive slab cracking, severely spalled and patched.		
Loints failed     Recycle and/or rebu		
Patching in very poor condition.	ld	
Severe and extensive settlements or front heaves.	ld	
Restricted speed.	ild	
1 • Extensive potholes. Total reconstruction	ild	
Almost total loss of pavement integrity.		

<sup>\*</sup> Note: Individual pavements will not have all of the types of distress listed for any particular rating. They may have only one or two types.